




Hydrogreen  
Energy



## TECHNICAL DATA SHEET

Reference: eCoCell-TiFF-40

Typical Properties	Units	Value
GDL thickness	mm	0.40
Porosity	%	60-75
Though plane permeability, Gurley method	Seconds	<1
Size	mm	300x300



HYDROGREEN ENERGY  
[www.hydrogreenenergy.com](http://www.hydrogreenenergy.com)  
(+34) 965 661 828  
[info@hydrogreenenergy.com](mailto:info@hydrogreenenergy.com)

Avenida de la Industria, 13-15 • 03690 San Vicente del Raspeig • Alicante